

## Strong points

DCP is an exceptional paper for an exceptional result. A quality document needs a quality paper, and valorises your customers.

DCP is the ideal base paper for all documents containing more colour illustrations than text. Its high whiteness and perfectly smooth surface contribute to high quality colour reproduction.

Available in a wide range of sizes and substances, DCP offer a complete range: white, ivory, coated, recycled; with a coordinated range of envelopes and available in 2500 sheets non stop boxes (5 times more sheets than a ream).

DCP is perfect for copiers, colour laser printers and colour inkjet printers. It is Colorlok certified by HP, which guarantees a very quick drying time for very vivid colours and crisp outlines.

## Technical specifications

|                   |                    |      |      |      |      |      |      |      |      |      |      |                     |
|-------------------|--------------------|------|------|------|------|------|------|------|------|------|------|---------------------|
| Grammage          | g/m <sup>2</sup>   | 80   | 90   | 100  | 120  | 160  | 200  | 250  | 280  | 300  | 350  | NF EN ISO 536       |
| Thickness         | μm                 | 93   | 98   | 108  | 128  | 164  | 202  | 230  | 258  | 276  | 322  | NF EN ISO 534       |
| Bulk              | cm <sup>3</sup> /g | 1,16 | 1,06 | 1,08 | 1,07 | 1,03 | 1,01 | 0,92 | 0,92 | 0,92 | 0,92 | NF EN ISO 534       |
| Brightness        | CIE                | 170  | 170  | 170  | 170  | 170  | 170  | 170  | 170  | 170  | 170  | NF ISO 11475        |
|                   | ISO                | 116  | 116  | 116  | 116  | 116  | 116  | 116  | 116  | 116  | 116  | ISO 2470-2          |
| Bekk smoothness   | s                  | 100  | 150  | 150  | 150  | 150  | 150  | 140  | 140  | 130  | 110  | NF ISO 5627         |
| Absolute humidity | %H <sub>2</sub> O  | 4,5  | 4,5  | 4,5  | 4,5  | 4,5  | 4,5  | 4,5  | 4,5  | 4,8  | 4,8  | NF EN ISO 20287     |
| Relative humidity | % ln the air       | 30   | 30   | 30   | 30   | 30   | 30   | 30   | 30   | 35   | 35   | Sword measurement   |
| Opacity           | %                  | 93   | 95   | 96   | 98   | >99  | >99  | >99  | >99  | >99  | >99  | NF ISO 2471         |
| Formation index   | Index on 120       | 96   | 114  | 114  | 114  | 114  | 111  | 110  | 110  | 110  | 110  | Kajaani measurement |

These values are not contractual.  
Revision date : 22/05/2017

## Certifications:

### Paper

### Mill



80 à 160g

NF EN 12281

ISO 9706

ISO 14001

ISO 9001