

<b>AVERAGE CHARACTERISTICS</b>			
<b>GRADE</b>	<b>Lyreco colours</b>		
<b>Fibre composition</b>	<b>ECF</b>		
<b>Medium</b>	<b>neutral</b>		
<b>Substance</b>	<b>160</b>	<b>g/m<sup>2</sup></b>	<b>NF EN ISO 536 NFQ 03 019</b>
<b>Thickness</b>	<b>210</b>	<b>microns</b>	<b>NF EN ISO 534 NFQ 03 016</b>
<b>Bulk</b>	<b>1,31</b>	<b>cm<sup>3</sup>/g</b>	<b>NF EN ISO 534 NFQ 03 016</b>
<b>Bendtsen smoothness</b>	<b>180</b>	<b>ml/min</b>	<b>ISO 8791-2 NF Q 03-049</b>
<b>Absolute humidity</b>	<b>5,50</b>	<b>%H<sub>2</sub>O</b>	<b>NF EN ISO 20287 NFQ 03 003</b>
<b>Relative humidity</b>	<b>42</b>	<b>in the air</b>	<b>sword</b>
<b>Permanence</b>	<b>ISO 9706</b>		<b>NF EN ISO 9706</b>