

COPY 1

Carta a superficie naturale, fabbricata con il 100% di cellulosa E.C.F. di legno proveniente da boschi, i cui responsabili attuano i principi e le misure per garantire una gestione sostenibile delle foreste.
 Il prodotto è Acid Free, con riserva alcalina, a garanzia di lunga conservazione conformemente alla norma ISO 9706.
 Altissimo grado di bianco. Qualità eccellente. Altissime prestazioni per copie di prestigio. Idonea per fotocopie, stampa laser, ink-jet e fax a carta naturale. Misure di Whiteness effettuate con Elrepho.

Uncoated paper, made with 100% of bleached pulp E.C.F. manufactured from trees, whose producers comply with methods and policy to guarantee a sustainable management of forest. FSC MIX CoC 000010
 The product is Acid Free, with alkaline reserve, guaranteeing long life according to ISO 9706.
 Extremely high grade of white. Excellent quality. Extremely high performance for prestige copies. Suitable for photocopies, laser printing, ink-jet and faxing.

CARATTERISTICHE - PROPERTIES	METODOLOGIA - METHOD	U.M.	TARGET	Min.	Max.
Umidità Assoluta Moisture Content	ISO 287 E.d.P.	%		3,5	5,5
Grammatura Grammage	UNI EN ISO 536 I.O. 10 P44 004	g/m ²	80,0	78,0	82,0
Spessore Thickness	ISO 534 I.O. 10 P44 005	microons	103,0	98,0	108,0
Assorbimento acqua [Cobb] Water absorptiveness [Cobb]	ISO 535 I.O. 10 P44 010	g/m ²			30,0
Grado di Bianco Brightness	ISO 2470 I.O. 10 P44 006	%	115,0	113,0	117,0
C.I.E. Whiteness C.I.E. Whiteness	ISO 11475 I.O. 10 P44 006		172,0	169,0	175,0
Opacità Opacity	ISO 2471 I.O. 10 P44 006	%		91,0	
Ruvidità [Bendtsen] Roughness [Bendtsen]	ISO 8791/2 I.O. 10 P44 007	ml/1'		160,0	300,0