

AVERAGE CHARACTERISTICS			
GRADE	Lyreco colours		
Fibre composition	ECF		
Medium	neutral		
Substance	80	g/m2	NF EN ISO 536 NFQ 03 019
Thickness	107	microns	NF EN ISO 534 NFQ 03 016
Bulk	1,34	cm3/g	NF EN ISO 534 NFQ 03 016
Bendtsen smoothness	150	ml/min	ISO 8791-2 NF Q 03-049
Absolute humidity	5,00	%H2O	NF EN ISO 20287 NFQ 03 003
Relative humidity	38	in the air	sword
Permanence	ISO 9706		NF EN ISO 9706

AVERAGE CHARACTERISTICS			
GRADE	Lyreco colours		
Fibre composition	ECF		
Medium	neutral		
Substance	160	g/m²	NF EN ISO 536 NFQ 03 019
Thickness	210	microns	NF EN ISO 534 NFQ 03 016
Bulk	1,31	cm³/g	NF EN ISO 534 NFQ 03 016
Bendtsen smoothness	180	ml/min	ISO 8791-2 NF Q 03-049
Absolute humidity	5,50	%H₂O	NF EN ISO 20287 NFQ 03 003
Relative humidity	42	in the air	sword
Permanence	ISO 9706		NF EN ISO 9706