

Average characteristics

Grade	Papiers Clairefontaine		
Certification	PEFC		
Fibre composition	ECF		
Medium	neutral		
Substance	80	g/m ²	NF EN ISO 536 NFQ 03 019
Thickness	108	microns	NF EN ISO 534 NFQ 03 016
Bulk	1,35	cm ³ /g	NF EN ISO 534 NFQ 03 016
Whiteness	170	CIE	NF ISO 11475 NFQ 03 099
	116	ISO	NFQ 03 039 ISO 2470
Bendtsen smoothness	160	ml/min	ISO 8791-2 NF Q 03-049
Absolute humidity	4,50	%H ₂ O	NF EN ISO 20287 NFQ 03 003
Relative humidity	30	dans l'air	sabre
Opacity on paper background	93	%	NF ISO 2471 NFQ 03 040
Kajaani formation	91		
Permanence	ISO 9706		NF EN ISO 9706